



A Member of the  Hargreaves Group of Companies

Rocfuel Premium Quality Wood Pellets

Typical Analysis

Size (diameter mm)	6mm
Total Moisture %	8.2
Ash %	0.7
Volatile Matter %	76.6
Fixed Carbon %	14.4
Sulphur %	0.01
Gross Calorific Value kJ/kg	18531
Net* Calorific Value kJ/kg	17169
D.A.F. Calorific Value kJ/kg	20360
D.A.F. Volatile Matter %	84.2
Mechanical Durability %	99.0
Ash Fusion(°C): Initial Deformation	1280
Hemisphere	1350
Flow	1370

**For more information about
Rocfuel premium quality wood pellets
call our team on: 01977 664 784
or email: enquiries@coal4energy.co.uk**